


DERBICOAT LAPFIX HP

Base-Sheet with Self-adhesive Overlaps

Composition of the membrane :

- ▶ DERBICOAT LAPFIX HP is a base sheet composed of an elastomeric bitumen blend, a glass / non-woven polyester reinforcement, a polyethylene film on the underside & a macroperforated polyethylene film on the topside.
- ▶ DERBICOAT LAPFIX HP is characterised by the presence on each side of a **longitudinal self-adhesive lap (width 13 cm)** protected by a siliconized film.



Technical characteristics

	Test method	Expression of result	Values	Units
Cold bending	EN 1109	MLV	- 25	°C
Tensile strength L/T	EN 12311-1	MDV (+/- 20%)	500/400	N/5 cm
Elongation at break L/T	EN 12311-1	MDV (+/-15)	40/55	%
Tear resistance L/T	EN 12310-1	MDV (+/- 20%)	200/200	N

MLV : Manufacturer Limited Value

MDV : Manufacturer Determined Value



Ecological

Special characteristics

DERBICOAT LAPFIX HP is a base sheet especially developed to be applied as a **loosely laid** or **mechanically fixed** flame barrier on **heat-sensitive supports** and/or that are **incompatible with cold-bonding**.

Presentation of the product

	Test method	Units	Expression of result	Values
Thickness	EN 1848-1	mm	MDV (+/-0.2)	2
Length	EN 1848-1	m	MLV	12.73
Width	EN 1848-1	m	MLV	1.10
Surface		m ²	MLV	14
Roll weight		kg	MDV (+/-2)	29
Number of rolls per pallet				25
Maximum storage time				12 months

Storage

Rolls must be carried and stored in a vertical position. The floor must be regular and free of sharp objects. Keep the rolls away from humidity and at a temperature between 10 and 25°C. Maximum storage time of the product : 12 months

